

METHOD OF TEST FOR THEORETICAL MAXIMUM RELATIVE DENSITY OF BITUMINOUS PAVING MIXTURES

LS-264 R27
ASTM D2041/D2041M - 11

3. APPARATUS

- 3.1 BEAKERS OR VESSELS: Stainless steel vessel, 4000 ml capacity, no spout..... _____
- 3.2 BALANCE: 4000 g capacity with an accuracy of ± 0.1 g..... _____
- 3.3 RIFFLE SPLITTER: For splitting hot mix samples. Recommended width of the individual chutes is approximately 38 mm for all types of paving mix..... _____
- 3.4 WIRE BASKET: Made from copper, stainless steel, or brass wire mesh, 160 ± 5 mm diameter x 180 ± 5 mm high to contain sample and beaker when weighing in water..... _____
- 3.5 WIRE: Thin as possible to suspend the basket from the balance. The use of fishing line leaders has been found to be satisfactory..... _____
- 3.6 VACUUM CELL: Stainless steel beaker or vessel fitted with a plexiglass top..... _____
- 3.7 PUMP: Vacuum - capable of maintaining a residual pressure in the vacuum cell of at least 30 mm of Hg..... _____
- 3.8 FILTERING FLASKS: Three 1000 ml Erlenmeyer filtering flasks with rubber stoppers..... _____
- 3.9 RESIDUAL PRESSURE MANOMETER: To be connected directly to the vacuum vessel and which should be capable of measuring residual pressure below 30 mm of Hg (see Note 1)..... _____
- Note 1: The use of a non-mercury device for the purpose of measuring the residual pressure is permitted if its accuracy is certified by the manufacturer or verified through the use of a traceable standard..... _____
- 3.10 MANOMETER OR VACUUM GAUGE: Suitable for measuring the vacuum being applied in close proximity of the pump. This is required to check the reading given by the residual pressure manometer..... _____
- 3.11 MANIFOLD: Standard 19 mm (0.75 in) I.D. galvanized water pipe fitted with up to 4 quick action valves and a bleeder valve..... _____
- 3.12 BLEEDER VALVE: Needle valve to control flow of air into the system for pressure control..... _____
- 3.13 SILICA GEL: Tell tale (3 mm – 1mm size)..... _____
- 3.14 TUBING: Rubber, vacuum, minimum 6.4 mm (0.25 in) I.D..... _____
- 3.15 TROWEL: Metal, garden type..... _____
- 3.16 CONSTANT TEMPERATURE WATER BATH: Capable of maintaining a temperature of $25 \pm 1^\circ\text{C}$ _____
- Note 2: Residual pressure in the vacuum vessel, measured in millimetres of mercury, is the difference in the height of mercury in the Torricellian leg of the manometer and the height of mercury in the other leg of the manometer that is attached to the vacuum vessel..... _____
- Note 3: One residual manometer may serve two vacuum vessels through the use of a two position three port valve (show in Figure 3 so that the residual pressure in each vessel may be measured alternately and independently of the other during the test)..... _____

METHOD OF TEST FOR THEORETICAL MAXIMUM RELATIVE DENSITY OF BITUMINOUS PAVING MIXTURES

LS-264 R27
ASTM D2041/D2041M - 11

Note 4: The Torricellian vacuum leg of the manometer occasionally acquires one or more bubbles of air that introduce error into the residual pressure reading. By the addition of the vacuum gauge this error can often be quickly detected by the differences between two vacuum measurements. Other potential problems such as partial restriction of the vacuum line in the silica gel can be detected in this way._____

4. SAMPLE SIZE

4.1 For mix design work and for loose field samples, the size of the test sample shall be governed by the 'Designated Large Sieve' size/mix type and shall conform to the requirements as shown in the following table:

Size of Test Sample

Mix Type	Designated Large Sieve Size (mm)	Minimum Mass of Sample (kg)
HL 2	2.36	0.5
SMA 9.5 Superpave 9.5	4.75	1.0
HL 1, HL 3, HL 3A, DFC, OFC, SMA 12.5, Superpave 12.5, 12.5FC1, 12.5FC 2	9.5	1.5
HL 4 (Binder and Surface)	13.2	1.5
Superpave 19.0, SMA 19.0	12.5	2.0
HL 8, MDBC, HDBC	16.0	2.0
Superpave 25.0	19.0	3.0
Superpave 37.5	25.0	4.0

4.2 The Designated Large Sieve is a sieve size specifically designated for testing purposes.

5. PREPARATION OF MIX DESIGN SAMPLES

5.1 The following assumes that the desired blend of aggregates has been determined, and a weigh card prepared. Also, the aggregates have been dried, and split into sieve fractions....._____

5.2 Arrange the individually sized coarse aggregate(s) and fine aggregate(s) in bags or in suitable containers on a bench, in order of decreasing sieve sizes....._____

The pass 2.36 mm from the coarse aggregate(s) and from the fine aggregate(s) shall be placed in separate flat-bottomed pans of appropriate size....._____

Using the flat-bottom scoop, weigh up, into separate pans for each test specimen, a sufficient quantity of oven-dried sample of the selected aggregates, so that the total mass will yield a sample of the specified size....._____

METHOD OF TEST FOR THEORETICAL MAXIMUM RELATIVE DENSITY OF BITUMINOUS PAVING MIXTURES

LS-264 R27
ASTM D2041/D2041M - 11

Place the aggregates in an oven maintained at a temperature not exceeding 28°C above the mixing temperature specified by the proprietor of the asphalt cement (AC) product..... _____

Heating time shall be a minimum of 16 hours, normally overnight..... _____

5.3 Preheat the mixing bowl in the same oven as the aggregate..... _____

5.4 Preheat the metal trowel and spatula on the hot plates or in an oven..... _____

5.5 Heat the AC to the mixing temperature specified by the proprietor of the AC using either an oven or hot plate..... _____

The AC should not be held at the mixing temperatures for more than 1 hour prior to its use..... _____

Suitable shields, baffle plates, or sand pads shall be used on the surface of the hot plate to prevent localized overheating..... _____

5.6 When the AC has reached the desired temperature, remove the container of aggregate from the oven, and quickly place it in the mixing bowl that has been previously tared on the balance..... _____

If the aggregate mass is not within ± 1 g of the originally batched mass prior to overnight heating, adjust the batch by the addition of preheated pass 2.36 mm material from the primary fine aggregate.... _____

Using the mixer, dry mix the aggregate for 15 seconds..... _____

5.7 After dry mixing, form a crater in the centre of the aggregate in the bowl..... _____

quickly add in the calculated amount of AC to give the desired AC content, and mix for 45 seconds or until the aggregate is coated. Do not mix longer than 1.5 minutes..... _____

Report any mixing problem such as coating of aggregate or balling of mix..... _____

5.8 At the end of the wet mixing cycle, using the pre-heated spatula, scrape as much of the mix as possible from the mixing paddle and scraper blade..... _____

5.9 Spread the mixture into the metal trough using a back and forth motion. Scrape all of the loose mixture in the bowl into a flat pan..... _____

5.10 Place the mixture into a metal pan of sufficient size to yield a spread rate of 20-22 kg/m², cover with aluminum foil or other suitable cover, and place in an oven maintained at 135°C for 2 hours. _____

Stir the mix occasionally during this period. For the design of Superpave mixes, the mixture shall not be covered with foil and the conditioning shall be in an oven maintained at the compaction temperature (see Note 7)..... _____

5.11 Following this conditioning period, allow the mix to cool to room temperature. During the cool down period, separate the particles by hand, taking care to avoid fracturing the aggregates, so that the particles of the fine aggregate portion are not larger than 6.3 mm..... _____

Note 7: The mixing and compaction temperatures are typically supplied by suppliers or proprietors of the AC. See Figure 1 for details..... _____

Note 8: While the determination of maximum theoretical relative density can be done for any AC content, the precision of the test is best when the mixture is close to the design asphalt content... _____

Also, the test shall be done in duplicate or triplicate..... _____

METHOD OF TEST FOR THEORETICAL MAXIMUM RELATIVE DENSITY OF BITUMINOUS PAVING MIXTURES

LS-264 R27
ASTM D2041/D2041M - 11

6. PREPARATION FROM LOOSE FIELD SAMPLES

6.1 Obtain loose field samples in accordance with specified procedures. Plate or loose mix samples shall be reduced to the proper size (See ASTM D2041). Two methods of reducing the field sample to the testing size are acceptable: quartering or splitting using a riffle splitter.....

Testing shall be done in duplicate.....

Note 9: When the test sample is greater than 3000 g, each sample may be split into two halves placed in two separate beakers and vacuum cells. Results from the two halves of the sample shall be combined and recorded as one.....

6.1.1 Quartering:

Warm the field sample to achieve sufficient workability for quartering.....

A conventional oven maintained at 110°C or a microwave oven (see Note 8) may be used for this purpose.....

The surface upon which the sample is to be reduced should be flat, non-abrasive, non-absorptive and of sufficient area to provide for uniform quartering. Heat lamps may be used to keep the surface warm (see Note 9).....

The sample shall be mixed on the surface until uniform, then quartered, and opposite quarters removed. This process is to be repeated until the testing size is obtained.....

Note 10: Caution: Frequent mixing may be necessary to prevent localized overheating when using a microwave oven to heat paving mixtures. Also, the presence of metal particles in some mixtures may render the microwave oven unsafe for the heating of these mixtures.....

Mixes made with polymer modified AC will have to be heated to a temperature higher than 110°C to achieve sufficient workability. The actual temperature should be the minimum required to achieve this and should be determined by trial and error.....

Note 11: If required, 'Pam' or equivalent used in minimal quantities has been found suitable in preventing the sample from adhering to the surface. Motor oils must not be used for this purpose.....

6.1.2 Riffle Splitter:

Warm the field sample to achieve sufficient workability for splitting. A conventional oven maintained at 110°C or a microwave oven (see Note 8 above) may be used for this purpose.....

The mix may agglomerate if it is too cold or stick to the splitter if too hot. A temperature range of 90°C to 110°C has been found to be generally satisfactory. Heat lamps may be used to keep the walls of the riffle splitter warm (see Note 10 above).....

Chutes shall be cleaned after each split.....

6.2 Spread the mixture out on a rectangular pan, dry to constant mass in an oven maintained at a temperature of 110 ± 5°C and allow to cool to room temperature.

Constant mass is defined as no change in mass in excess of 0.1% for each 30 minute drying period.....

During the cool down period, separate the particles by hand, taking care to avoid fracturing the aggregates, so that the particles of the fine aggregate portion are not larger than 6.3 mm.....

METHOD OF TEST FOR THEORETICAL MAXIMUM RELATIVE DENSITY OF BITUMINOUS PAVING MIXTURES

LS-264 R27
ASTM D2041/D2041M - 11

7. PREPARATION FROM COMPACTED PAVEMENT SAMPLES

7.1 Dry the entire core or sawn sample to a constant mass by placing the pan containing the material in an oven maintained at a temperature of $110 \pm 5^\circ\text{C}$

Constant mass is defined as no change in mass in excess of 0.1% for each 30 minute drying period._____

Note 12: Pavement samples used in this test may also require the determination of their bulk relative density. Such samples may contain residual moisture from the sawing/coring operation. These samples should have their mass in water and their surface dry mass determined prior to drying (see LS-262)_____

7.2 After the core or sawn sample has been dried to constant mass, trim to a depth approximately equivalent to the "Designated Large Sieve" size of the particles to remove the particles which were cut during the coring/sawing operation.....

7.3 Allow the material to cool down to room temperature. During this cool down period, separate the particles by hand, taking care to avoid fracturing the aggregates, so that the particles of the fine aggregate portion are not larger than 6.3 mm.....

Note 13: If, for a mix with a "Designated Large Sieve" size of 16 mm, the mass of the pavement cored/sawn sample after trimming is less than 1000 g, the MRD shall not be determined. For cores, this would represent a sample of less than 25.4 mm (1") thickness and would not be considered typical_____

8. PROCEDURE

8.1 Set up the equipment for this test as shown in Figures 2 or 3.....

Transfer the loose mixture into a vacuum cell which has been previously calibrated for its mass in air and water.....

Add sufficient water at approximately 25°C to completely cover the sample.....

8.2 Place the plexiglass top on the vessel ensuring a tight seal.....

Gradually reduce the pressure to 30 ± 1 mm Hg.....

Maintain this pressure for 15 minutes with periodic (or continuous) agitation to ensure that all the air has been removed.....

At the end of the specified time, release the vacuum slowly.....

8.3 Suspend the vessel and contents in the water bath and determine the mass after 10 ± 1 minute immersion.....

Record the temperature of the water in the water bath if different from 25°C

Note 14: For testing multiple samples, the vessels and their contents may be submerged in a water bath at about 25°C , so that the total time of immersion (in the water bath and during subsequent weighing) is 10 ± 1 minutes.....

8.4 For porous aggregates or aggregates that are not thoroughly sealed by a bituminous film, refer to ASTM D2041 to conduct a supplemental procedure.....

METHOD OF TEST FOR THEORETICAL MAXIMUM RELATIVE DENSITY OF BITUMINOUS PAVING MIXTURES

LS-264 R27
ASTM D2041/D2041M - 11

9. CALCULATION

9.1 Calculate the theoretical maximum relative density (MRD) as follows: _____

$$MRD = (D - E) / [(D - E) - (G - H)]$$

Where:

D = mass of beaker and mixture in air, g

E = mass of beaker in air, g G = mass of beaker and mixture in water at test temperature, g

H = mass of beaker in water at test temperature, g

9.2 If the temperature varies from 25°C, a correction to the MRD will be made in accordance with the following.....

$$MRD (@ 25^{\circ}C) = MRD (at test temperature) \times K$$

Where:

K = correction factor listed in Table 1 for the test temperature

11. GENERAL NOTES AND PRECAUTIONS

11.1 Most aggregates will absorb water if extensive asphalt stripping occurs while the test sample is under vacuum.

11.2 If the vacuum pump cannot produce the residual pressure required (30 ± 1 mm Hg), check the pressure at the vacuum pump. If this pressure is less than 30 mm Hg and the pressure at the vacuum vessel is not, check for blockage of the system in the silica gel tube or flask. If pressure at the pump is higher than the 30 mm Hg check the cell lids, valves and all tubing and connections for air leaks. Use heavy vacuum grease and/or hose clamps to seal connections. Do NOT use grease on the lid seals.....

11.3 Check the oil level in the vacuum pump regularly. If water is present, drain the old oil, remove all moisture, and add clean oil.....

11.4 Dry silica gel has a deep blue colour. When the silica gel is pink in colour, it is wet, and should be removed from the flasks and dried in an oven overnight so that it can be re-used.....

11.5 When determining the mass of the sample in water, the basket and beaker must be completely immersed.....

11.6 After vacuuming, care must be taken to avoid exposing the mixture to air before the mass in water is measured.....

11.7 When determining the mass in water, check that no air bubbles are adhering to the wire basket or beaker (particularly under the lip).....

11.8 It is not necessary for the water to boil continuously to ensure that all the air has been removed. Table 2 shows that water at 25°C will not boil unless the residual pressure is 23.756 mm Hg or lower.....

METHOD OF TEST FOR THEORETICAL MAXIMUM RELATIVE DENSITY OF BITUMINOUS PAVING MIXTURES

LS-264 R27
ASTM D2041/D2041M - 11

11.9 Increasing the temperature of the water in the vacuum cell above 30°C will give rise to higher boiling rates, which will adversely affect the ability to maintain the system at the required absolute pressure.....

11.10 The water in the vessel should be maintained as close to 25°C as possible. Where more than one vessel is being used, vessel pressures will show slightly different pressures unless the temperature of the water is approximately the same in each vessel.....

COMMENTS