

SOUNDNESS OF AGGREGATES BY USE OF MAGNESIUM SULPHATE LS-606 R33

1. SCOPE

1.1 This method covers the testing of aggregates to determine their resistance to disintegration in saturated solutions of magnesium sulphate. It furnishes information helpful in judging the soundness of aggregates subject to weathering action, particularly when adequate information is not available from service records.

3. APPARATUS

3.1 SULPHATE TANK: A suitably constructed three-compartment tank, one compartment for solution make-up, one for the test solution, and the third for washing the completed test samples.....
The test solution compartment shall contain suitable refrigeration and heating units capable of controlling the temperature of the magnesium sulphate solution within $\pm 1.0^\circ\text{C}$ of the required temperature.....

Note 1: Immersion type mercury contact thermo-regulators reading to 0.05°C controlling Jumo electronic relays are suitable for this purpose.

3.2 SIEVES: With square openings of the following sizes conforming to OPSS specifications, Table 1.....

Table 1

Coarse Series	Fine Series
4.75 mm	300 μm
9.50 mm	600 μm
13.2 mm	1.18 mm
16.0 mm	2.36 mm
19.0 mm	4.75 mm

3.3 WIRE BASKETS: For immersing the samples of aggregates in the solution. The baskets shall bear a number or other means of identification.....

The baskets shall be made of copper wire or stainless steel and of appropriate mesh so as allow free access of the solution to the sample and drainage of the solution from the sample without loss of aggregate (e.g. 19 - 9.5 mm aggregate use sieve mesh 6.7 mm, 9.5 - 4.75 mm aggregate use sieve mesh 2.36 mm)

3.4 BALANCES: For fine aggregate, a balance or scale accurate within 0.1 g over the range required for this test; for coarse aggregate, a balance or scale accurate within 0.1% or 1 g, whichever is greater, over the range required for this test.....

3.5 MECHANICAL CONVECTION OVEN: The oven shall be capable of being continuously heated at $110 \pm 5.0^\circ\text{C}$, and the rate of evaporation at this range of temperature shall be at least 25 g/h for 4 h, during which period the doors of the oven shall be kept closed.....

This rate shall be determined by the loss of water from 1-litre Griffin low-form beakers, each initially containing 500 g of water at a temperature of $21 \pm 2.0^\circ\text{C}$, placed at each corner and the centre of each shelf of the oven.....

The evaporation requirement is to apply to all test locations when the oven is empty except for the beakers of water.....

3.6 HYDROMETER: Capable of determining the relative density of the test solution, conforming to the requirements of ASTM E100.....

SOUNDNESS OF AGGREGATES BY USE OF MAGNESIUM SULPHATE LS-606 R33

3.7 LABORATORY CONTROL AGGREGATE: A supply of reference aggregate is available from the Soils and Aggregates Section of the Materials Engineering and Research Office at the Ministry of Transportation (soils-aggregates@ontario.ca)..... _____

4. PREPARATION OF SOLUTION

4.1 Prepare a saturated solution of magnesium sulphate by dissolving a U.S.P. or equal grade of the salt in water at a temperature of $40 \pm 3.0^{\circ}\text{C}$. Add sufficient salt of either the anhydrous (MgSO_4) or the crystalline ($\text{MgSO}_4 \cdot 7\text{H}_2\text{O}$, Epsom salt) form to ensure saturation and the presence of excess crystals when the solution is ready for use in the tests..... _____

Thoroughly stir the mixture during the addition of salt and stir the solution at frequent intervals until used..... _____

To reduce evaporation and prevent contamination, keep the solution covered at all times when access is not needed..... _____

Allow the solution to cool $21 \pm 1.0^{\circ}\text{C}$ _____

Again stir and allow the solution to remain at the designated temperature for at least 48 h before use..... _____

Prior to each use, break up the salt cake, if any, in the container, stir the solution thoroughly, and determine the relative density of the solution..... _____

When used, the solution shall have a relative density not less than 1.295 nor more than 1.308.... _____

Discard a discoloured solution or filter it and check for relative density..... _____

Note 2: For the solution, 350 g of anhydrous salt or 1230 g of heptahydrate per litre of water are sufficient for saturation at 23°C . However, since these salts are not completely stable, with the heptahydrate being the more stable of the two and, since it is desirable that an excess of crystals be present, it is recommended that the heptahydrate be used and in an amount of not less than 1400 g/L of water.

Note 3: Freshly mixed sulphate solutions have low pH values, which may result in a higher loss of material for aggregates containing carbonate minerals. When testing these types of materials, the pH value of freshly mixed solutions should be checked for pH (with either a pH meter or pH paper, range 5 - 7) and neutralized by the addition of a suitable additive.

5. PREPARATION OF SAMPLE

5.1 FINE AGGREGATE: Fine aggregate for the test shall be passed through a 4.75 mm sieve..... _____

The test sample shall be obtained from the materials to be tested by use of a sample splitter or the method of quartering and shall weigh approximately 2500 g..... _____

The sample is then washed on a 300 μm sieve and dried to a constant mass..... _____

The sample is separated into the sizes shown in Table 2 by sieving in a mechanical sieve shaker for a period of 8 to 12 min. _____

From the fractions obtained in this manner, select samples of sufficient size to yield 100 g after sieving to refusal (in general, a 110 to 120 g sample will be sufficient). The samples are then re-sieved to refusal on the same sieves using a mechanical sieve shaker for a period of 12 min..... _____

Weigh samples consisting of 100 ± 0.1 g from each of the separated fractions after final sieving and place in separate containers for the test..... _____

Note 4: Sieving to 'refusal' means that no particles pass the sieve during 1 min. of continuous

SOUNDNESS OF AGGREGATES BY USE OF MAGNESIUM SULPHATE

LS-606 R33

sieving. No hand manipulation of particles is allowed.

Table 2

Passing Sieve	Retained on Sieve
600 µm	300 µm
1.18 mm	600 µm
2.36 mm	1.18 mm
4.75 mm	2.36 mm

Should the sample have less than 30% retained on the 300 µm sieve, it is deemed to be too fine and no test is done on any fraction..... _____

If any fraction constitutes less than 5% of the sample, it shall not be tested..... _____

5.2 COARSE AGGREGATE: Coarse aggregate for test shall consist of material from which sizes finer than the 4.75 mm sieve have been removed..... _____

Separate the sample into the different sizes shown in Table 3 by sieving to refusal. Weigh out quantities of the different sizes shown in Table 3..... _____

If any fraction constitutes less than 5% of the sample, it shall not be tested..... _____

Table 3

Size Fractions	Min. Mass of Size Fractions, g	Sieve Used to Determine Loss, mm
9.5/R4.75	300	4.75
P13.2/R9.5	500	9.5
P19/R13.2	1500	13.2
P37.5/R19	2500 Consisting of 26.5 mm to 19 mm (33%) 37.5 mm to 26.5 mm (67%)	19
P63/R37.5	5000 Consisting of 53 mm to 37.5 mm (33%) 63 mm to 53 mm (67%)	19

6. PROCEDURE

6.1 FINE AGGREGATE: Place each fraction in a separate suitable wire basket..... _____

6.2 COARSE AGGREGATE: Place the 9.5 mm to 4.75 mm fraction, 13.2 mm to 9.5 mm fraction, 19.0 mm to 13.2 mm fraction in three suitable wire baskets respectively..... _____

Place combined fractions larger than 19 mm in one or more baskets as required..... _____

6.3 STORAGE OF SAMPLES IN SOLUTION: Immerse the samples in the prepared solution of magnesium sulphate for not less than 16 h or more than 18 h in such a manner that the solution covers them to a depth of at least 15 mm..... _____

Maintain the samples immersed in the solution at a temperature of 21 ± 1.0°C for the immersion period..... _____

The volume of solution shall be at least 20 times greater than the total sample volume..... _____

6.4 DRYING SAMPLES AFTER IMMERSION: After the immersion period, remove the samples from the solution, drain for 30 ± 5 min., and place in drying oven..... _____

Dry at 110 ± 5.0°C until constant mass has been achieved, usually 6 to 8 h..... _____

SOUNDNESS OF AGGREGATES BY USE OF MAGNESIUM SULPHATE LS-606 R33

Drying time may be established as follows: with oven containing the maximum sample load expected, check the loss in mass of samples by removing and weighing them in the baskets, without cooling, at intervals of 2 to 4 h. Make enough checks to establish required drying time for the least favourable oven location and sample condition.

Constant mass will be considered to be achieved when the loss is less than 0.1% of sample mass in 4 h of drying. When constant mass is achieved, allow samples to cool to room temperature and immerse in solution..... _____

Note 5: As the number of cycles progresses, the drying time required increases due to loss of drying efficiency because of the accumulation of salt adhering to particles, increase of surface area due to breakdown, and differences in surface area due to particle sizes.

6.5 NUMBER OF CYCLES: Repeat the process of alternate immersion and drying for 5 cycles..... _____

7. QUANTITATIVE EXAMINATION

7.1 After completion of the final cycle, and after the sample has cooled, wash the sample free from the magnesium sulphate as determined by the reaction of the wash water with a 3% (by mass) barium chloride (BaCl₂) _____

Wash by circulating hot tap water (40 to 60°C) in their containers..... _____

A continuous flow of fresh hot water shall be maintained throughout the washing period. In the washing operation, the sample shall not be subjected to impact or abrasion that may tend to break up particles..... _____

After the magnesium sulphate has been removed, dry the samples to a constant weight at 110 ± 5.0°C..... _____

7.2 FINE AGGREGATE: Sieve the fine aggregate over the same sieve on which it was retained before the test, nesting the sieves so that the finest is on the top and the coarsest is on the bottom..... _____

Sieve in a mechanical sieve shaker for a period of 12 min..... _____

Weigh the material retained on each sieve and record each amount on the Fine Aggregate Report Card (Figure 1 in the LS) _____

7.3 COARSE AGGREGATE: Sieve material over the sieve according to Table 3. Sieve material larger than 63 mm over the same sieve on which it was retained before the test..... _____

Sieve only sufficiently to assure that all undersize material passes the sieves..... _____

Weigh the material retained on each sieve and record each amount on the Coarse Aggregate Report Card (Figure 2 in the LS)..... _____

8. QUALITATIVE EXAMINATION

8.1 A qualitative examination may be done on coarse aggregate samples to determine the mode of breakdown, i.e. splitting, disintegration, crumbling, cracking, flaking, etc. This examination is not done routinely by MTO. Samples are held in storage for some time after the test. If there are conflicting or "surprising" results in this test, the samples may be recalled and examined in an effort to resolve problems of this nature.

SOUNDNESS OF AGGREGATES BY USE OF MAGNESIUM SULPHATE LS-606 R33

9. CALCULATION

9.1 Calculate the percent loss for each fraction in the magnesium sulphate soundness test as follows:

..... _____

$$\text{percent loss} = \frac{\text{original mass} - \text{mass retained after test}}{\text{original mass}} \times 100$$

9.1.1 Calculate the percent loss to one decimal place..... _____

9.2 Calculate the weighted percent loss for each fraction as the product of the percentage (based on the "as-received" coarse aggregate sample mass or "as-received" fine aggregate sample mass) of each fraction and the percent loss for that fraction..... _____

9.2.1 Calculate the weighted average value of the as-received sample as the sum of the weighted percent loss for each fraction divided by 100..... _____

9.2.2 For the purpose of calculating the weighted average, consider any sizes (not tested) that contain less than 5% of the as-received sample to have the same values as the average of the next smaller and the next larger size or if one of these sizes is missing, to have the same value as the next larger or smaller size, whichever is present..... _____

For fine aggregates, sizes smaller than the 300 µm sieve shall be assumed to have zero percent loss_____

10. USE OF LABORATORY CONTROL AGGREGATE

10.1 At least every week in which a sample is tested, an appropriate sample of coarse and/or fine reference aggregate shall also be tested.

Table 4 – Grading of Fine Reference Aggregate

Sieve Fraction	Percent Retained
Minus 300 µm	24
600 to 300 µm	25
1.18 mm to 600 µm	22
2.36 mm to 1.18 mm	18
4.75 mm to 2.36 mm	11

10.2 Control Chart Use: The weighted average loss of the last 20 samples of reference material shall be plotted on a control chart in order to monitor the performance of the laboratory..... _____

10.3 The mean loss of the control aggregates are provided on the labels..... _____

11. REPORT

The report shall include the following:

11.1 The weighted average loss of the reference sample, tested closest to the time at which the aggregate sample was tested, to 1 decimal place..... _____

11.2 The weighted average loss of the last 20 samples of reference material on a control chart... _____

11.3 Report the loss in percent of each fraction of the sample tested to 0.1%..... _____

11.4 Report the weighted loss in percent of the sample tested to the nearest 0.1%..... _____

SOUNDNESS OF AGGREGATES BY USE OF MAGNESIUM SULPHATE LS-606 R33

12. PRECAUTIONS

12.1 Wire baskets shall be examined after each test for defects in the mesh..... _____

12.2 Extreme care must be taken when immersing the fine aggregate samples as often some of the particles float on the solution due to surface tension. Carefully, with the fingers, sink these particles into their baskets when this happens..... _____

COMMENTS