

SUPERPAVE GYRATORY COMPACTION – PLANT MIX (ON QC)

IMPORTANT NOTE: (New this year) The preparation of compacted specimens is to the Design Gyration Level only. No compaction to the maximum gyration level is required.

1. PLANT SUPERPAVE SAMPLES (PSS)

Two boxes of Superpave Plant Mix for two different mixes (I and II), namely **I-PSS-x for the 19.0mm mix** and **II-PSS-x for the 12.5mm mix** have been provided

2. MAXIMUM SPECIFIC GRAVITY (G_{mm})

Determine the G_{mm} of each mix type using LS-264. Report the value of each of the two replicates (i) and (ii) to three decimal places.

3. GYRATORY COMPACTION

The specimen preparation parameters for this testing are as follows:

	19.0mm (I-PSS)	12.5mm (II-PSS)
Mass of individual gyratory specimen, g	4900±40	4950±40
Recompaction temperature, °C	144	142
Initial number of gyrations, N_{ini}	9	8
Design number of gyrations, N_{des}	125	100

For each mix type, prepare two specimens to the **design number of gyrations**

4. BULK DENSITY AND % G_{mm} (Compaction Degree)

Prepare specimens, determine the bulk density and complete all necessary calculations, **using applicable Ontario LS and AASHTO procedures**, to obtain % G_{mm} at N_{ini} , and the % Air voids at N_{des} .

Report the values of bulk densities to three decimal places.

Report values of % G_{mm} to one decimal place.

The Gyratory Report Form must be completed **online and submitted by January 7 2022**. An example of a completed report form is shown below. Your form will appear slightly different as testing requirements have been changed (Compaction to N_{max} has been removed).

Important Change for 2022: Your lab's worksheets must be submitted through the portal with your proficiency report. Please combine all worksheets for each portal report into a single pdf prior to uploading. You are required to keep all original worksheet hard copies in a secure dedicated location such as a sealed envelope that is available to CCIL upon request. Do not courier/mail/fax/e-mail the worksheets to CCIL.

DO NOT send reports and worksheets by fax



2020 Asphalt Reporting Form Gyratory Plant Mix

Gyratory Plant Mix Report - Certification Program

- ▶ CCIL Confidential Lab # CCIL 999
- ▶ Lab Name: Demo Lab
- ▶ Tested by:
 - Lab Technician
 - Supervisor / Manager
 - Not listed

Please specify

Super Technician

Gyratory Plant Mix Report

Test	A-PS-xxx (i)	A-PS-xxx (ii)	- Avg	B-PS-xxx (i)	B-PS-xxx (ii)	- Avg
MSG (G _{mm} by LS-264)	2.615	2.625	2.620	2.600	2.610	2.605
BRD @ N _{det}	2.525	2.535	2.530	2.520	2.526	2.523
BRD @ N _{max}	2.546	2.566	2.556	2.540	2.550	2.545
% G _{mm} @ N _{ini}	89.2	89.6	89.4	88.8	89.2	89.0
% G _{mm} @ N _{max}	97.4	97.8	97.6	97.7	97.7	97.7
% Air Voids (@ N _{det})	3.4	3.4	3.4	3.1	3.2	3.2

Compactor Calibration

Internal Angle (1.16 deg.)

Comments